

BITUMINOUS PRIMER

A SEALER OR PRIMER FOR ALL POROUS AND NON-POROUS SURFACES

PRINCIPAL USES

As a primer for all Bituminous systems, including Deltaplast and Scudoplast.

SPECIFICATION

Surfaces to be coated with Pro-Struct 201 Bituminous Primer at a rate of $\pm 3-5\text{m}^2/\text{litre}$, depending on surface porosity. On very porous surfaces, a second coat may be necessary.

MIXING

Stir well before use, using a flat paddle.

INSTRUCTIONS

Surfaces must be clean, sound and dry. All surfaces must be free from oils and grease and laitance removed from cementitious surfaces. Pro-Struct 201 is a one part bituminous primer and is ready for use. Application must be done by brush or roller. Primer must be allowed to dry completely, prior to overcoating to prevent entrapment of solvents.

CAUTION

Brushes are to be cleaned by using Pro-Struct 105 Epoxy Brush Cleaner and washed off with soap and water. Clean hands with a solvent-wetted rag. Adequate ventilation must be allowed for and do not smoke or use a flame during application. Avoid prolonged contact with skin and inhalation as product contains aromatic and aliphatic solvents.

TYPICAL PROPERTIES AT 25°C

Colour	Black
No. of Components	1
Coverage	$\pm 3-5\text{m}^2/\text{litre}$
Apply Over	Clean, dry surface
Flash Point	30°C
Drying Time	2-4 Hours
Volume Solids	35%
Application Temperature	10°C to 35°C
Overcoat Time	4-6 Hours
Shelf Life	12 Months

Safety: Material is flammable and the necessary safety precautions need to be taken in the handling of his product.