

**QUICKSEAL POLYSULPHIDE JOINT SEALANT**

**HIGH RESIN CONTENT**  
**LONG LIFE PERFORMANCE**  
**NON-SAG, NON-TACKY CURED SURFACE**  
**SUITABLE UNDER CONTINUAL WET CONDITIONS**  
**QUICK SETTING TIME**

**PRINCIPAL USES**

Sealing of vertical or horizontal concrete joints, window and doorframes and cladding in high rise buildings. This trafficable joint sealant is suitable in areas exposed to intense UV and weather conditions, water retaining structures and sewage works. Not suitable for use in swimming pools.

**RESISTANCE**

Resists most aqueous solutions, alkalis, aliphatic hydrocarbons and many chemicals found in industry. For specific resistance information, contact StonCor Africa Technical Department.

**JOINT DESIGN**

It is recommended that joints be designed so that the movement does not exceed 25% of the joint width. The joint configuration should be such that the ratio of joint width to depth be 2:1, except in the case of smaller joints where the minimum recommended depth of 6mm is applicable. It is advisable to ensure that joints are parallel sided as departure from this could impair the service life of the sealant. It is essential that a bond breaking backup cord be inserted into the joint to support the sealant and to control the depth.

**SPECIFICATION**

All joints to be sealed with Pro-Struct 749 Quickseal Polysulphide Joint Sealant mixed and applied onto primed surfaces in accordance with Manufacturer's detailed instructions.

**INSTRUCTIONS**

Before application of Pro-Struct 749 Quickseal Polysulphide Joint Sealant, attention should be given to ensure that the joint is clean, dry and sound. All dust, laitance or unsound material should be removed by mechanical means. Concrete surfaces should be at least 28 days old prior to sealing being undertaken. Tape edges of joints with masking tape to ensure a clean, tidy joint. Prime the faces of the joint with Stonprime 639 Primer for porous surfaces. Place bond breaking backup strip in position. Allow primer to dry before application of the sealant is started. Remove the activator pack and follower plate from the kit and mix the contents of the activator pack with base by slow speed (150 to 250 RPM) mechanical stirring for 5 minutes until a uniform colour and consistency is obtained.

**Detailed attention to mixing of the components must be given and the need for complete blending cannot be over-emphasised.** Replace the follower plate in the can and load the sealant gun.

The sealant should be applied in such a manner as to ensure freedom from air pockets and to obtain good contact with the joint faces. This will be assisted by tooling the sealant with the tool being lubricated with a minimum amount of water. On completion of work and at regular intervals during sealing operations, all equipment to be cleaned with Pro-Struct 105 Brush Cleaner.

**See also Instruction Sheet "Handling of Epoxy Products"**

**TYPICAL PROPERTIES AT 25°C**

Finish	Slight Sheen
Colour	Grey
Consistency	Thick paste
Volume Solids	100%
Theoretical Coverage	Refer to guide
No. of Components	2
Mix Ratio by Volume	Mix as supplied
Pot Life	30-60 Minutes
Apply Over	Primed sound surfaces
Apply By	Pressure Gun – 749 Pour - 744
Curing Time	24 Hours – initial set 7 Days – full cure
Thinner	Nil
Shelf Life	12 Months
Max. Service Temperature	-30°C to 50°C
Application Temperature Range	15°C to 35°C
Shore A Hardness	25±10

# APPLICATION INSTRUCTIONS

These instructions are not intended to show product recommendations for specific service. They are issued as an aid in determining correct surface preparation, mixing instructions and application procedure. It is assumed that the proper product recommendations have been made. These instructions should be followed closely to obtain the maximum service from the materials.

## JOINT QUANTITY MATERIAL GUIDE NO ALLOWANCE HAS BEEN MADE FOR WASTAGE

### JOINT SEALANTS

JOINT SIZE (mm)	LINEAR METRES/LITRE
5 x 5	40,0
6 x 6	28,0
10 x 10	10,0
12 x 10	8,3
15 x 10	6,7
18 x 10	5,6
20 x 10	5,0
24 x 12	3,5
25 x 12	3,3
30 x 15	2,2

**CAUTION: MAY CONTAIN FLAMMABLE SOLVENTS.** KEEP AWAY FROM SPARKS AND OPEN FLAMES. IN CONFINED AREAS WORKMEN MUST WEAR FRESH AIRLINE RESPIRATORS. HYPERSENSITIVE PERSONS SHOULD WEAR GLOVES OR USE PROTECTIVE CREAM. ALL ELECTRONIC EQUIPMENT AND INSTALLATIONS SHOULD BE MADE AND GROUNDED IN ACCORDANCE WITH THE NATIONAL ELECTRICAL CODE. IN AREAS WHERE EXPLOSION HAZARDS EXIST, WORKMEN SHOULD BE REQUIRED TO USE NONFERROUS TOOLS AND TO WEAR CONDUCTIVE AND NONSPARKING SHOES



**StonCor Africa (Pty) Ltd**

Co. Reg. No. 1996/001848/07

Tel: +27 (0)11 254 5500

Website: [www.stoncor.co.za](http://www.stoncor.co.za)

E-mail: [stoncorsa@stoncor.com](mailto:stoncorsa@stoncor.com)