

RITVER ALUZINC PRIMER Product No. PS1600

Ritver Aluzinc Primer is a mono component self etching primer designed to provide subsequent adhesion to non ferrous substrates particularly aluminum and galvanized substrates. The product reacts with the substrate thereby creating a chemical and mechanical bonding. It can be over coated directly with a wide range of paints.

USE

Substrates: Galvanized Steel and Aluminum
Area of Use: Interior and exterior.

SPECIFICATIONS

Properties

Finish	: Matt Finish
Colour	: White, Gray
Specific gravity	: 1.1 +/- .05%
Solids (% by volume)	: 35 +/- 2%
Diluent	: PT7001
Flash point	: 28C
Spread Rate	: 14 square meters per liter theoretical at 25 microns
Drying Time (30° C)	: 15 minutes touch dry : 40 minutes to recoat
Recommended DFT	: 40 to 50 microns

SURFACE PREPARATION

The product is very tolerant to moderate surface preparation. Always ensure that the surface is free of oil, grease, dust and other contaminants. Sand rusted surface and a slight solvent wash with a clean rug is enough for good adhesion.

APPLICATION METHODS

Adequate ventilation should always be observed when applying Ritver Aluzinc Primer for reasons of health and safety and to ensure proper drying of the material. Never apply this product in adverse weather conditions such as when the temperature is below 5C or when the humidity level is above 90%. The surface temperature should always be kept at not less than 3 degrees above dew point. The addition of 30-50% PT7001 can be added when using conventional spray. Do not over thin the product as this may result in sagging and run downs especially in vertical applications.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

Date Revised: 01st Jan 2012

RITVER ALUZINC PRIMER Product No. PS1600

TYPICAL PAINT SYSTEM

Ritver Aluzinc Primer	PS 1600 RITVER Topcoats	40-50 microns 35-50 microns
-----------------------	----------------------------	--------------------------------

STORAGE & SHELF LIFE

Under dry and cool condition, storage stability can be sound up to 18 months in original sealed containers.

HANDLING

Disposal: As per the guidance and legislations of the local Authority e.g. by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Not applicable

SAFETY PRECAUTION

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream.

Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray.

MSDS is available on request for the safe handling of this product.

FIRST AID

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved industrial cleaner. DO NOT USE solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.