

QUICK DRYING ENAMEL Product No. PS3201

Ritver Quick Drying Enamel is based on a special grade Alkyd resin containing anticorrosive pigments. It is used as a top coat for many applications in the industries of steel and other OEM type as well as sign makers especially for protecting the metals and other steel structures against corrosion. Its main advantage lies however lies in the fact that being quick drying and accepts recoat ability.

USE

Substrates: Steel furniture, steel frame, steel drum or other metal substrates.
Area of Use: Interiors and Exteriors.

SPECIFICATIONS

Properties

Finish	: Smooth/Glossy. (Available in S.glossy and Matt on request)
Colour	: All colours as per Ritver shade card
Specific gravity	: 1.41+/- .005
Mixed Solids (% by volume)	: 52 ± 2
Diluent	: Xylene
Flash point	: 27°c
Spread Rate:	
While the spread rate is directly dependant on the surface profile and also the type of undulations it has, as a thumb rule Ritver Quick Drying Enamel would cover 10 – 12 meters per lit.	
Drying Time (30° C)	: Set to touch: 1.5 – 2 hours. : Ready for Recoat: app 6 hours.
Recommended DFT	: 1 mist coat followed by a good full coat. App 35 - 40 mic.

SURFACE PREPARATION

A good surface preparation and following the method statement / recommended system procedure of Ritver is an ideal recommendation for the application of **Ritver Quick Drying Enamel**.

For Metals & Steel Surfaces:

Achieve a good and clean surface by removing all contaminants by cleaning & drying. A laitance free surface should be achieved by good sweep blast or a wire brush. Apply one coat of **Ritver Quick Drying Primer** and proceed after drying. Apply one good coat or two nominal coats with a spray or a suitable roller and obtain the desired coverage.

Exclusions for successful application include perpetually wet surfaces and also large cavities on wood, metal or concrete surfaces.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

QUICK DRYING ENAMEL Product No. PS3201

APPLICATION METHODS

Adequate ventilation is an ideal situation as it helps in drying and the good application itself. Avoid high humid conditions i.e., >95% when condensation is likely to interfere and also when the surface temperature is at least 3°C above dew point.

Application: To be done by conventional roller or spray at 2000 – 2500 psi for airless spray or 50 – 60 psi for conventional spray). Nozzle size: 0.015 - 0.018 inches.

One can add 5 - 10% of **Ritver QD Thinner** for ease of application of brush/roller/or spray viscosity.

Caution: Over diluting would result in sag and run downs.

TYPICAL PAINT SYSTEM

<p>Ritver Quick Dry Enamel</p> <ul style="list-style-type: none"> • Or as per Ritver technical advice 	<p>Ritver Synthetic Red Oxide Primer Ritver synthetic undercoat Ritver Quick Dry Enamel</p>	<p>1 coat 1 coat 2 coats</p>
--	--	--------------------------------------

STORAGE & SHELF LIFE

Under dry and cool condition, Storage stability can be sound up to 18 months in original sealed containers.

HANDLING

Disposal: As per the guidance and legislations of the local Authority e.g., by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Contains aromatic hydrocarbons and 27°C.

QUICK DRYING ENAMEL Product No. PS3201

SAFETY PRECAUTION

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. Other industrial practices are applicable. Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray.

MSDS is available on request for the safe handling of this product.

FIRST AID

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved Industrial cleaner. DO NOT USE solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.