

POLYACRYLIC PIGMENTED- [MATT]

Product No. **AW34X0**

[For Exterior Wood]

Two-components polyacrylic clear varnish matt, endowed with waxy effects and outstanding resistance to abrasion , provides very high UV resistance , good washability , abrasive detergent and hard weather conditions.

USES

Designed for exterior wood that can withstand especially for outdoor applications .

CHARACTERISTICS

Properties

- Very Good Adherence
- Very Good Plasticity
- Very Good Hardness

Appearance	: Matt
Color	: Pigmented
Specific gravity	: 1.12 Kg/lit [± 0.025]
Weight Solids	: 54% [± 2]
Weight Solid Blended	: 30% [± 2]
Flash point	: 21°C

Drying Time

Dust Free	: 1 hr.
To Touch	: 2 hrs. at 25°C at 25 μ DFT
Interval Coats	: 6 hrs.
To Sand After	: 24 hrs. at 25°C at 25 μ DFT
Deep Drying	: 24-48 hrs. at 25°C

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. Surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning.

Wooden floor surface must be sanded and cleaned thoroughly. On exotic timbers, apply properly the PU isolant PI 280 as first coat. Sand the isolant before application of Polyacrylic for exterior wood. Product can be utilized as base coat and top coat.

To achieve a concrete surfaces, arrange well the top then apply the polyacrylic for the protection of the surfaces.

POLYACRYLIC PIGMENTED- [MATT]

Product No. **AW34X0**

[For Exterior Wood]

PRODUCT PREPARATION

CATALYST

by weight 50%	CP019	by volume 50%
------------------	-------	------------------

Pot Life 4 hrs. @25°C

Stir product well with a flat paddle. Add the correct quantity of hardener and stir till homogeneous. Thin to required viscosity. For details of spray equipment contact Ritver Technical Services Department.

Dilution

Roller: Dilute with PU thinner [TP292] at 30-40%.

Brush: Dilute with PU thinner [TP292] at 30-40%.

In case of hot and humid climate, add 5 -10% of PU retardant thinner [TP222].

APPLICATION METHODS

Depends on the finishes required but in general an appropriate rate is 150 gr / sq.m. / coat. The number of coats depends on the surface preparation the porosity of the substrate, and the finish required.

Following Treatments

By roller or brush, stir very well the part "A" to obtain distribution of matting agent contents in the product. Mix the two components and wait 20 – 30 min for pre-reaction. Apply 2-3 coats with sanding in between coats.

Important:

- Respect time of interval coats
- Do not apply if the environment temperature is under 10°C. Even the temperature of the varnish must be over 10°C.

CLEANING

Cleaning

Clean all tools and equipment immediately after use with [TC010] Tool Cleaning.

POLYACRYLIC PIGMENTED- [MATT]

Product No. **AW34X0**

[For Exterior Wood]

PACKING & STORAGE

Available in 5Kg, 25Kg.

Store in a cool and well ventilated place. Keep away from direct sunlight. Minimum one year in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is flammable and must not be exposed to naked flames.

Use only in well ventilated areas. In case of insufficient ventilation during application wear suitable respiratory equipment. Do not breathe vapor / spray. In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. In case of contact with skin, wash immediately with soap and water or a recognized skin cleanser.

Keep away from sources of ignition. No Smoking. Keep out of reach of children.