

MELAMINE TOPCOAT BLACK- [MATT]

Product No. **DT74XX**

[Acid Curing – Standard Grade]

Standard Grade two components Acid curing topcoat Black Matt finishes, modified with exceptional resin and high solid contents, exhibits good clarity, plasticity, scratch resistance and very good build, indicated to varnish modern and old style furniture, frames and wooden manufacturers of different nature.

USES

Suitable for interior use and could be used as sealer and topcoat at the same time due to its excellent sanding properties.

SPECIFICATIONS

Properties

- Standard Grade
- Flexibility
- Good Hardness
- Good Covering
- Plasticity
- Scratch Resistance

Available in the following Shades

DT7400	DM 6%	[±1]
DT7410	MT 12%	[±3]
DT7430	SM 30%	[±5]
DT7450	SG 50%	[±5]
DT7470	GL 70%	[±5]

Appearance	: Matt
Color	: Black
Specific gravity	: 1.01 Kg/lit.

Weight Solids : Approx. 52% [± 2]

Weight solid blended : Approx. 48% [± 2]

Flash point : 21 °C

Drying Time

Dust Free	: 15 min.
To Touch	: 25 min. @25°C at 25µ DFT
Interval Coat	: 2 hrs. @25°C at 25µ DFT
Deep Dry	: 24 hrs.

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. The surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning.

Always check compatibility with required [stains / sealers] or similar pretreatment. Good sanding to substrate utilizing paper no. [120] is essential, as is adequate sanding and removal of dust prior of application of [DT74XX] Ritver Melamine Cure Black –Matt. Apply the White Melamine Cure Primer in 2-3 cross coats according to the required coverage. Followed (after drying) with sanding paper no. [220] and [400] to create perfection. Remove the dust and apply [DT74XX] as per required shade.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

MELAMINE TOPCOAT BLACK- [MATT]

Product No. **DT74XX**

[Acid Curing – Standard Grade]

PRODUCT PREPARATION

CATALYST

by weight		by volume
10%	CD070	10%

Pot Life 6 hrs. @ 25°C

Stir product well with a flat paddle. Add the correct quantity of hardener and stir till homogeneous. Thin to required viscosity. For details of spray equipment contact Ritver Technical Services Department.

Dilution

Utilize [TN190] NC Thinner depending on the application system used. In general 25% thinner is added to achieve an application viscosity; this is suitable for spray application.

For Curtain Coater dilute with 20% [TN190] NC Thinner.

In case of hot climate and higher humidity add 5% of [TN122] NC Retardant Thinner.

APPLICATION METHODS

Depends on the finishes required but in general an appropriate rate is 130g / sq. m. The number of coats depends on the surface preparation, the porosity of the substrate, and the finish required. This quality can be reduced if applied over polyester.

CLEANING & CAUTION

Cleaning

Clean all tools and equipment immediately after use with [TC010] Tool cleaning.

Caution

Do not use when humidity levels may cause surface condensation (maximum 85%), during rainy conditions or if temperatures are likely to fall below 5°C during application and drying. Protect from frost.

PACKING & STORAGE

Available in 3.5Ltr, 18Ltr.

Store in a cool and well ventilated place. Keep away from direct sunlight. Minimum one year in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is flammable and must not be exposed to naked flames.

Use only in well ventilated areas. In case of insufficient ventilation during application wear suitable respiratory equipment. Do not breathe vapor / spray.

In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. In case of contact with skin, wash immediately with soap and water or a recognized skin cleanser.

Keep away from sources of ignition. No Smoking. Keep out of reach of children.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

Date Revised: 01st Jan 2012