

NC TOPCOAT WHITE - [MATT] Product No. **NT13XXC**

[Standard Grade]

Standard Grade single pack pigmented Nitrocellulose Topcoat Matt finish modified with special resin exhibits good covering and scratch resistant. It is designed for furniture frames and manufactured wood of different nature.

USES

Suitable for Internal Use. The fast drying time combined with desirable physical properties makes it ideal for mass production. Easy application by conventional spray, airless and curtain coater.

SPECIFICATIONS

Properties

- Standard Grade
- Softness
- Good Hardness
- Good Covering
- Plasticity
- Good Adhesion

Available in the following Shades

NT1300C	DM 6%	[±1]
NT1310C	MT 12%	[±3]
NT1330C	SM 30%	[±5]
NT1350C	SG 50%	[±5]
NT1370C	GL 70%	[±5]

Appearance	: Matt
Color	: White
Specific gravity	: 0.990 Kg/lit [±0.025].
Weight Solids	: Approx. 27 % [± 2]
Flash point	: 21°C
Drying Time	
Dust Free	: 10 min.
To touch	: 30 min. @25°C at 25µ DFT
Deep dry	: 4 hrs. @25°C at 25µ DFT
To Pack	: 12 hrs. @25

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. The surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning.

Always check compatibility with required [primer] or similar pretreatment. It is essential to sand the applied primer by utilizing paper no [400], as an adequate light sanding and dust removal prior of application of [NT13XXC] Ritver NC topcoat pigmented –Matt.

NC TOPCOAT WHITE - [MATT] Product No. **NT13XXC**

[Standard Grade]

PRODUCT PREPARATION

Stir product well with a flat paddle. Thin to the required viscosity in both instances ensuring the product is homogeneous after stirring. For details of spray equipment contact Ritver Technical Services Department.

Dilution

Utilize NC Thinner depending on the application system used. In general 100% thinner is added to achieve an application viscosity. This is suitable for conventional spray. In case of high humidity climate add 3% [TN122] NC Retardant thinner.

APPLICATION METHODS

Applicable to apply the Topcoat pigmented range on solid wood and veneer substrate treated with NC pigmented base coat or Polyurethane. For product affinity, it is recommended to use primer surfacer before the application of the final top coat.

Depends on the finishes required but in general an appropriate rate is 140 g / sq. m./ coat. The number of coats depends on the surface preparation the porosity of the substrate, and the finish required.

CLEANING & CAUTION

Cleaning

Clean all tools and equipment immediately after use with [TC010] Tool Cleaning.

Caution

Do not use when humidity levels may cause surface condensation (maximum 85%), during rainy conditions or if temperatures are likely to fall below 5°C during application and drying. Protect from frost.

PACKING & STORAGE

Available in 3.5Ltr, 18Ltr, 200Ltr.

Store in a cool and well ventilated place. Keep away from direct sunlight. Minimum one year in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is flammable and must not be exposed to naked flames.

Use only in well ventilated areas. In case of insufficient ventilation during application wear suitable respiratory equipment. Do not breathe vapor / spray.

In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. In case of contact with skin, wash immediately with soap and water or a recognized skin cleanser.

Keep away from sources of ignition. No Smoking. Keep out of reach of children.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

Date Revised: 01st Jan 2012